



Nano-Silica Technology
for Concrete

ARMOURTECH NEW FLOOR STD FINISH

PERFORMANCE SPECIFICATION FOR POLISHING USING THE LYTHIC
EXPOSED AGGREGATE FLOOR SYSTEM –

Dust proofed Abrasion resistant floor with Light Shine.

This specification is provided as a service and is intended to be used as a guideline for preparing the appropriate project specific specification sections.

The quality and level of Diamond Polishing is always the starting point of a good polished floor.

EXECUTION

SURFACE CONDITIONS:

Examine substrate for conditions affecting performance of finish.

Correct conditions detrimental to timely and proper work. Do not proceed until unsatisfactory conditions are corrected.

A. Verify that base slab is clean of any mastic or adhesives from previous floor coverings, loose debris, dirt, mildew, oils and grease and efflorescence, curing and latent construction materials.

B. New concrete must be in place a minimum of 28 days or as directed by the Manufacturer before application can begin.

APPLICATION

1. Grind to expose aggregate.
2. Float cementitious skim coat product over the floor to fill pinholes.
3. At approx 120-200 grit grind apply **Lythic STD Densifier**. Apply with airless sprayer.
4. Keep surface wet for 15 - 20 minutes and let dry. No need clean up excess.
5. Approx 1 hr after application polishing can continue to your usual ending grit.



Nano-Silica Technology
for Concrete

armourtech

Final step Lythic Protector System (optional)

Lythic Protector is recommended, as a contaminant barrier and to increase the shine and depth of colour.

Surface should be completely clean and dry before application of Lythic Protector.

Using a low-pressure pump sprayer, apply Lythic Protector in a **light mist**. Using a damp micro fibre or flat cotton pad applicator, spread Lythic Protector in a **thin film coat** using a figure 8 motion to reduce streaking and to prevent puddling.

Once completely dry use floor stripper pads to smooth out the Protector barrier (Black Stripper Pad) Then burnish with Hogshair pad or similar/ **OR** use **diamond impregnated pads** will do the same as the 2 step process as described above. Burnishing with a minimum **2000** RPM machine.

For this burnish achieve a concrete surface Temp of **32C**. A hand held digital temperature device is ideal for this purpose and can be purchased from **Jaycar** 16-18 Fisher Crescent Mt Wellington, Ph. 0800 452 922 model number is **QM7215**

Allow finished floor to cure for 24 hours before allowing regular foot traffic. Wait 72 hours before leaving standing water. Protector is only for Indoor usage.

Cure finished floor for 24 hours before allowing regular foot traffic. Do not allow standing water to remain on the surface for the first 72 hours.

Reapplying Protector and burnishing can renew the shine.

1. Applicable procedures must be followed as recommended by the product manufacturer.

C. FINAL PROTECTION

1. Following completion of the final polishing, surface must be covered to protect from other trades. Cover with breathable product, such as kraft paper, "Ram Board". Do not cover with rosin paper. Plywood protection to have 4 mil plastic slip sheet barriers between wood and slab.

www.concretesealers.co.nz