

## Diamond polish #1:

1. Grind with metal bond diamonds to expose aggregate.
2. Float cementitious skim coat product over the floor to fill pin holes.
3. Using diamonds after your next grind approx 400 grit apply **Lythic** Densifier as per instructions.
4. Let dry after the 20 minutes dwell time. No need to clean up excess.
5. Then polish to your usual ending grit.
6. Apply one thin application of **Protector** (optional). After 1 or 2 hours burnish. Achieve Temp of 32C. Again, the pad you use will have an impact on the shine.

## Diamond polish #2

1. Grind with metal bond diamonds to expose aggregate.
2. Float cementitious skim coat product over the floor to fill pinholes.
3. Using diamonds after your next grind approx 400 grit apply **Lythic** Densifier per instructions
4. Let dry after the 20 minutes dwell time. No need to clean up excess.
5. Then polish to your usual ending grit.
6. Apply one thin application of **Lythic XL Densifier**. Do not pour on floor, but rather either spray apply and spread or use pad applicator. Micro-fiber applicator will help prevent streaking an even layer application is important.

After drying, try either one, or all three of the next steps:

1. Go over area with final diamond again. Done
2. Go over area with final diamond and burnisher. Done
3. Go over area with just burnisher. Done
4. Apply one thin application of **Protector** (optional). After 1 or 2 hours burnish. Achieve Temp of 32C. The pad you use will have an impact on the shine.