

The HardwareFloor - Non-polished concrete: (no diamonds)

1. Clean surface with cleaner and some kind of agitation to remove any loose material.
2. Apply **Lythic** Densifier – keep wet for **15-minutes**
3. After it dries, remove dried material by cleaning again – using stripper pads and water
4. Apply **Lythic XL** Densifier – keep wet for **15-minutes**
5. After it dries, remove dried material by cleaning again – using stripper pads and water
6. Once dry you can burnish. Or you can apply Lythic Protector and then burnish with high-speed burnishing pad.

Optional Protector

Apply Lythic Protector. An even coverage is important. Use a microfiber mop or pad applicator. You can dilute more than normal and apply twice to get even coverage.

After 1 to 2 hours burnish. Burnish with high-speed burnishing pad. Achieve a surface Temp of 32C.

Cure finished floor for 24 hours before allowing regular foot traffic. Do not allow standing water to remain on the surface for the first 72 hours. Lythic Protector is intended for interior use.

This system is for durable, non-dusting, harder wear surface that may not want or need a high polish.